

P300

IMPREGNATING/MAINTAINING AGENT FOR FRESH AND EXISTING CONCRETE SURFACES

ADVANTAGES

- Ensures optimum proper curing and surface sealing of fresh concrete
- Reduces oil and water absorption
- Increases abrasion resistance
- Protects against dust
- Easy to apply
- Provides excellent aesthetics and an intense sheen to the concrete surface
- Reduces the appearance of micro-scratches
- Reduces chloride penetration
- Increases frost resistance by sealing

CHARACTERISTICS AND USE OF THE PRODUCT

- Solvent-based acrylic resin dispersion, colourless liquid
- Formulation used to impregnate, seal and harden newly installed concrete floors, both surface hardened and high quality concrete, including service yards, car parks and external roads
- P300 is also designed to impregnate old concrete substrates to strengthen and ensure watertightness
- It is particularly suitable to use P300 on a surface cured with Romix curing sprinkle

INSTRUCTIONS FOR USE AND APPLICATION

The surface should be free of free dirt (dust, debris, others) and standing water.

FRESH SUBSTRATE

Apply on the freshly trowelled surface with a spray or roller. The preparation is applied immediately after the final troweling and smoothing of the floor surface. The time of application is of the utmost importance. It is important to remember that freshly made flooring dries quickly, which results in shrinkage microscratches. Therefore, apply the treatment immediately after the mechanical treatment has been completed. If the area is particularly exposed to drying out due to high temperatures or draughts, it is recommended to cover the surface with a foil or geotextile after drying.

Due to its properties, P300 closes the micropores of the concrete, leaving a thin film that degrades as a result of natural use after the curing period.

OLD SUBSTRATE

When applying to an old substrate, adjust the amount of preparation to the absorption capacity of the substrate. Apply approximately 0.1 l/m² to the prepared cleaned substrate and wait until the substrate is completely dry. If you do not notice a clear glossy film, repeat the application, bearing in mind that the absorption capacity of the substrate has been considerably reduced, so the quantity of preparation should be correspondingly lower.

If the impregnated concrete is to be covered with other layers, e.g. resinous flooring, an adhesion test should be carried out, and if the material used requires direct contact with the concrete, the resulting layer should be removed mechanically (grinding, shot-blasting, milling).

The drying time depends on the application conditions. At 20°C, the surface is dry after 1-3 hours.

CLEANING AND MAINTENANCE OF A CONCRETE FLOOR

- **Si-Clean** – preparation for daily cleaning and care
- **Si-Wax** – self-gloss polymer paste
- **Si-Active Concrete Clean** – alkaline cleaner for basic cleaning and removal of heavy soiling

STORAGE AND TRANSPORT CONDITIONS

- Shelf life of P300 at 0-30°C is 12 months from date of manufacture
- Protect the product from fire and frost

PRECAUTIONS

- Follow the safety data sheet and instructions on the packaging.
- Product to be used outdoors or only in the open without the presence of third parties, protect from skin and eye contact
- P300 contains organic solvents

EFFICIENCY

- Depending on the absorbency of the substrate on existing concretes from 0.1 to 0.3 l per m²
- freshly poured concretes - consumption depends on weather conditions and ranges from 0.08 to 0.12 l per m²

Note: *The above information has been compiled to the best of our technical knowledge, but is not legally binding.*

Hygienic Approval No. B.BK.60111.0790.2022